

# SOUTHWEST RESEARCH INSTITUTE®

6220 CULEBRA ROAD 78238-5166 • P.O. DRAWER 28510 78228-0510 • SAN ANTONIO, TEXAS, USA • (210) 684-5111 • WWW.SWRI.ORG

CHEMISTRY AND CHEMICAL ENGINEERING DIVISION  
FIRE TECHNOLOGY DEPARTMENT  
WWW.FIRE.SWRI.ORG  
FAX (210) 522-3377



Registered to  
ISO 9001:2008

## FIRE PERFORMANCE EVALUATION IN ACCORDANCE WITH NFPA 259-13, *STANDARD TEST METHOD FOR POTENTIAL HEAT OF BUILDING MATERIALS*

**MATERIAL ID: *KREYSLER FIRESHIELD 285***

**FINAL REPORT**  
**Consisting of 5 Pages**

**SwRI® Project No.: 01.19582.01.306**  
**Test Dates: December 11 and 12, 2013**  
**Report Date: January 6, 2014**

**Prepared for:**

**Kreysler & Associates**  
**501 Green Island Road**  
**American Canyon, CA 94503**

Submitted by:

  
Eugene F. Horton  
Principal Engineering Technologist  
Material Flammability Section

Approved by:

  
Matthew S. Blais, Ph.D.  
Director  
Fire Technology Department

This report is for the information of the client. It may be used in its entirety for the purpose of securing product acceptance from duly constituted approval authorities. This report shall not be reproduced except in full, without the written approval of SwRI. Neither this report nor the name of the institute shall be used in publicity or advertising.



Benefiting government, industry and the public through innovative science and technology

## 1.0 INTRODUCTION

The objective of this test program was to perform a fire performance evaluation for Kreysler & Associates, located in American Canyon, CA. The material was identified by the Client as *Kreysler Fireshield 285*. The material was tested in accordance with National Fire Protection Association (NFPA) Standard 259, *Standard Test Method for Potential Heat of Building Materials*, 2013 Edition. Testing was conducted on December 11 and 12, 2013, at Southwest Research Institute's (SwRI) Fire Technology Department, located in San Antonio, Texas.

This test method is intended to measure and describe the properties of materials, products, or assemblies in response to heat and flame under controlled laboratory conditions and should not be used to describe or appraise the fire hazard or fire risk of materials, products, or assemblies under actual fire conditions. However, results of this test may be used as elements of a fire risk assessment which takes into account all of the factors which are pertinent to an assessment of the fire hazard of a particular end use. The results apply specifically to the specimens tested, in the manner tested, and not to similar materials, nor to the performance when used in combination with other materials.

## 2.0 TEST PROCEDURE

The gross and net calorific potential of materials are determined as described in NFPA 259-13. The apparatuses, specimen preparation, and test protocol are described in detail in this standard. There are two test procedures used in this standard to determine the potential heat of a material.

The first procedure is the oxygen bomb calorimeter test procedure. For this test, a specimen weighing nominally  $1.0 \text{ g} \pm 0.9 \text{ g}$  is placed in a metal crucible, which is then placed in a stainless steel bomb. If necessary, benzoic acid with a heat of combustion of 11,373 Btu/lb is used as a combustion promoter. The sample is tested in general accordance with ASTM D 5865-07a, *Test Method for Gross Calorific Value of Coal and Coke* (The NFPA 259-13 references ASTM D 3286, but this standard was withdrawn and replaced by ASTM D 5865). This procedure yields a gross heat of combustion. Two tests are conducted for repeatability. If the first two tests do not agree to within 10%, a third test is performed.

The second test procedure, the electric muffle furnace test procedure, requires a test specimen cut in the shape of a rectangular prism measuring  $13 \times 19 \times 64 \text{ mm}$  (W  $\times$  L  $\times$  H) height to be placed on the wire specimen holder, which is placed in the specimen container. The specimen container has a cap on one end and a hole on the other end, which allows fresh air to circulate around the test sample to promote complete combustion. The test sample is exposed to a temperature of  $750 \text{ }^\circ\text{C} \pm 10 \text{ }^\circ\text{C}$  for 2 hr with a regulated airflow supplied at  $47 \text{ cm}^3/\text{s}$  referenced to  $20 \text{ }^\circ\text{C}$  and 101 kPa, i.e., standard

temperature and pressure. After 2 hr, the test sample is removed from the furnace and placed in a desiccator to cool. Once the specimen has cooled to room temperature, the mass is measured.

If the mass of the residue remaining after the electric muffle furnace test procedure is not more than 5% of the initial mass of the test specimen, then the gross heat of combustion measured in the oxygen bomb calorimeter test procedure is considered to be the potential heat of the material tested.

If the mass of the residue is greater than 5% of the initial mass of the test specimen, then the residue must be tested according to the oxygen bomb calorimeter test procedure. Two tests must be performed, and if the results differ by more than 10%, a third test is performed. The potential heat of the material is the difference between the gross heat of combustion measured in the first test procedure and the gross heat of combustion of the residue (as defined in NFPA 259) from the second procedure.

The parameters measured are as follows:

*Gross Heat of Combustion ( $Q_{gr}$ )* – The amount of heat released by the complete combustion of a unit of mass of the material, corrected for the heats of formation of  $H_2NO_3$  and  $H_2SO_4$ , and for the heat of combustion of the firing wire and combustion promoter (if required). The gross calorific potential has a different value when combustion occurs in a constant pressure environment from that obtained in a constant volume environment. Tests are performed in a constant volume.

*Potential Heat ( $Q_p$ )* – The difference between the gross heat of combustion per unit mass of a representative specimen of the material and the heat of combustion per unit mass of any residue remaining after exposure of a representative specimen of the material to a defined heat source, i.e., muffle furnace, using combustion calorimetric techniques.

### 3.0 DESCRIPTION OF TEST SPECIMENS

Kreysler & Associates, located in American Canyon, CA, provided a material for testing in accordance with NFPA 259. Four specimens were received to test at SwRI on December 4, 2013. The material was identified by the Client as *Kreysler Fireshield 285* and is further described in Table 1.

**Table 1. Test Sample Description.**

| Material ID                    | Description                                  | Color | Nominal Received Dimensions (mm)* | Received Mass* |
|--------------------------------|--|-------|-----------------------------------|----------------|
| <i>Kreysler Fireshield 285</i> | FRP laminate with polymer concrete face coat | White | 152 × 152 × 7.6                   | 320.9 g        |

SwRI personnel prepared the specimens in accordance with NFPA 259. Samples were prepared with a combustion promoter. For the electric muffle furnace test procedure, specimens were cut to the appropriate dimensions (approximately 13 × 19 × 64 mm), per NFPA 259.

Samples were placed in a conditioned environment maintained at 23 °C ± 2 °C and 50% ± 5% relative humidity after preparing them at 150 °F for 72 hours in order to help comply with constant mass requirements, and at the additional request of the client, per the NFPA 259 standard. Constant mass was achieved on December 11, 2013.

#### 4.0 TEST RESULTS

The electric muffle furnace and the oxygen bomb calorimetry testing were conducted on December 11 and 12, 2013, and conducted by Alan Lowry, Senior Technician. Table 1 contains the test data set from the initial bomb calorimeter test procedure. Table 2 contains the test data from the Electric Muffle furnace and Table 3 includes the test data from the residue bomb furnace procedure.

**Table 1. NFPA 259 Bomb Calorimeter Results of Raw Material.**

|  | Run 1 | Run 2 | Average     |
|--|-------|-------|-------------|
| <b>Total Initial Mass (g)</b>            | 0.397 | .396  | 0.397       |
| <b>Final Mass (g)</b>                    | 0.397 | 0.396 | 0.397       |
| <b>Gross Heat of Combustion (Btu/lb)</b> | 3376  | 3365  | <b>3371</b> |

**Table 2. NFPA 259 Electric Muffle Furnace Results.**

|                         | Run 1   | Run 2   | Run 3   | Average |
|-------------------------|---------|---------|---------|---------|
| <b>Initial Mass (g)</b> | 22.207  | 22.333  | 23.321  | 22.587  |
| <b>Final Mass (g)</b>   | 14.533  | 14.528  | 15.249  | 14.770  |
| <b>Percent Residue</b>  | 65.45 % | 65.05 % | 65.39 % | 65.30 % |

**Table 3. NFPA 259 Residue Bomb Results From Muffle Furnace.**

|  | Run 1 | Run 2 | Run 3 | Average |
|--|-------|-------|-------|---------|
| <b>Initial Residue Mass (g)</b>          | 0.400 | 0.400 | 0.400 | 0.400   |
| <b>Combustion Promoter (g)</b>           | 0.400 | 0.400 | 0.400 | 0.400   |
| <b>Total Initial Mass (g)</b>            | .800  | 0.800 | 0.800 | .800    |
| <b>Final Bomb Mass (g)</b>               | 0.384 | 0.379 | 0.384 | .382    |
| <b>Gross Heat of Combustion (Btu/lb)</b> | 160   | -10   | 65    | 72      |

Two oxygen bomb test runs were performed, and the average gross heat of combustion was calculated. The percent difference less than 10%, so a third test was not run in accordance with the standard. The material residues from the electric muffle furnace test runs were greater than 5%; thus, a third residue test was run in the bomb calorimeter and electric muffle furnace. The potential heat of combustion was calculated according to the following equation:

$$P = G - cR$$

where  $P$  is the potential heat of combustion,  $G$  is the gross heat of combustion, as calculated by bomb testing of the raw material,  $c$  is the ratio of the weight of the residue to the weight of the initial sample from the muffle furnace exposure, and  $R$  is the gross heat of combustion of the residue. We find the potential heat of combustion of *Kreysler Fireshield 285* to be 3324 Btu/lb.